

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

D7

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷: C23C 8/02, 8/20, 8/22, 8/36, 8/44, 8/46	A1	(11) International Publication Number: WO 00/50661 (43) International Publication Date: 31 August 2000 (31.08.00)
(21) International Application Number: PCT/US99/18420 (22) International Filing Date: 12 August 1999 (12.08.99) (30) Priority Data: 09/133,040 12 August 1998 (12.08.98) US (71) Applicant (for all designated States except US): SWAGELOK COMPANY [US/US]; 29500 Solon Road, Solon, OH 44139 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): WILLIAMS, Peter, C. [US/US]; 3495 Edison Road, Cleveland Heights, OH 44121 (US). MARX, Steven, V. [US/US]; 2439 Belvoir Boulevard, University Heights, OH 44118 (US). (74) Agent: GUTT, Ronald, D.; Calfee, Halter & Griswold LLP, Suite 1400, 800 Superior Avenue, Cleveland, OH 44114 (US).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report.
(54) Title: LOW TEMPERATURE CASE HARDENING PROCESSES (57) Abstract A method for case hardening a chromium bearing nickel of ferrous based alloy, for example stainless steel, article, the method including the steps of activating the surface of the article; and carburizing the activated surface at a temperature below that temperature which would promote the formation of carbides. In one embodiment the surface is activated by disposing a layer of iron over the surface of the article.		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

LOW TEMPERATURE CASE HARDENING PROCESSES

Technical Field of the Invention

The present invention relates to processing techniques for articles of stainless steel and other alloys, such as, for example, tube coupling ferrules. More particularly, the invention relates to processes for case hardening such articles substantially without the formation of carbides.

Background of the Invention

As is well known, stainless steel is commonly used for many parts and assemblies. One example is a ferrule used as part of a fluid coupling for joining tube ends. The degree to which the stainless steel must be used will vary from application to application. In some high purity systems, for example in the semiconductor and biotechnology fields, lower carbon stainless steel such as 316L for example, is commonly used. Many chemistries for stainless steel are used, and other chromium bearing nickel or ferrous based alloys are known and used other than stainless steel.

One attribute of some stainless steel alloys is that they are relatively less hard than other steel alloy materials. As a result in some applications, such as ferrules, the stainless steel article or part is provided with a hardened surface, referred to generally and herein as case hardening. The concept of case hardening is to transform a relatively thin layer of material at the surface of the part by enrichment of carbon or other ingredients to make the surface harder than the base metal alloy. This disclosure is directed to case hardening of an article by enrichment by carbon. The article thus retains in bulk the desired

- 2 -

formability of stainless steel without the softness of the standard chemistry base metal at the article surface.

Stainless steel parts are case hardened by a process generally known as carburization. Carburization is a process by which carbon atoms are diffused in solution
5 into the surface of the article. Known case hardening processes are performed at high temperatures. However, carburization processes performed at temperatures greater than about 1000 °F (for stainless steel alloys) can promote the formation of carbides in the hardened surface.

It is desired, therefore, to provide new carburization processes for case hardening
10 chromium bearing nickel or ferrous based alloy articles and that does not promote the formation of carbides.

Summary of the Invention

In accordance with one embodiment of the invention, a method for case hardening a chromium bearing nickel or ferrous based alloy article includes the steps of activating
15 the surface of the article and carburizing the activated surface at a temperature below that temperature which would promote the formation of carbides. In one embodiment the activating step is carried out by disposing a layer of iron over the surface of the article.

These and other aspects and advantages of the present invention will be apparent to those skilled in the art from the following description of the preferred embodiments in
20 view of the accompanying drawings.

- 3 -

Brief Description of the Drawing

The invention may take physical form in certain parts and arrangements of parts, preferred embodiments and a method of which will be described in detail in this specification and illustrated in the accompanying drawing which forms a part hereof, and
5 wherein:

The drawing is an elevation in longitudinal cross-section of a conventional ferrule as an example of a type of article that has been case hardened using the exemplary processes of the present invention.

Detailed Description of the Preferred Embodiments

10 With reference to the drawing, a conventional ferrule 10 structure is illustrated wherein the ferrule has also been case hardened as set forth hereinafter. This ferrule 10 is but one example of countless many articles and parts that can be used with the present invention. While the invention is described herein with reference to a 316 type stainless steel ferrule, such description is intended to be exemplary in nature and should not be
15 construed in a limiting sense. The present invention finds application with any part or article made of a chromium bearing nickel or ferrous based alloy base metal that is to be case hardened.

Furthermore, although the preferred embodiments are described herein with specific reference to articles made of stainless steel alloys, such descriptions are
20 exemplary in nature and should not be construed in a limiting sense. The present invention is applicable to many types of chromium bearing ferrous or nickel based alloy

- 4 -

chemistries, including but not limited to alloy 316, alloy 316L and alloy 304 stainless steels, alloy 600, alloy C-276 and alloy 20 Cb, to name a few examples.

The ferrule 10 is illustrated in the drawing in partial cross-section only. This particular ferrule is a rear ferrule that is used as part of a two ferrule system. Such
5 ferrules and ferrule systems including the ferrule geometries are well known and are fully described in United States Patent Nos. 4,915,427 and 3,103,373, the entire disclosures of which are fully incorporated herein by reference.

The ferrule 10 is characterized by a tapered nose portion 12, a central body 14 and a rear drive surface 16. In a tube coupling, the rear drive surface 16 engages a wall of a
10 nut that axially drives the nose of the ferrule 10 into a rear camming mouth of a front ferrule (not shown). This action, among other things, causes the nose portion 12 of the ferrule 10 to be driven radially inward to grip a tube end. The geometry of the ferrule 10 illustrated in Fig. 1 is exemplary in nature and will vary substantially depending on the particular ferrule system. The ferrule 10 could also be used in a single ferrule system in
15 which case the nose portion 12 is driven into a camming mouth of a forward coupling element.

A common but not exclusive material for the ferrule 10 is 316 stainless steel. To enable driving the ferrule 10 into an enhanced grip of a tube end, it is desirable in some applications to case harden the ferrule 10. As used herein, case hardening means to
20 provide a relatively thin carburized layer at the surface of the ferrule 10 to increase the surface hardness as compared to the base metal used for the ferrule 10. Carburization is a

- 5 -

preferred method for case hardening the ferrule 10, and in accordance with one aspect of the present invention, low temperature carburization processes are used which permit case hardening of the ferrule 10 without the formation of carbides.

Carburization in general is a process by which carbon atoms are diffused into the base alloy in solution. In order to diffuse the carbon atoms into the stainless steel, the chromium oxide layer must be removed. This step is generally known as activation or de-passivation. The surface must be activated because the oxide layer presents a substantial barrier to carbon atoms. Once activated, the surface can be carburized by diffusion at an elevated temperature.

10 The diffusion process can be accelerated by performing the carburization at a high temperature, for example, greater than 1000 °F. However, such high temperature diffusion can readily and quickly produce carbides which are carbon/chromium molecules. Carbides tend to reduce the chromium of the base alloy in some cases.

In order to prevent or substantially eliminate the formation of carbides, the present invention contemplates carburization processes for case hardening that are performed at a temperature that is below a carbide promoting temperature. For many chromium bearing alloys such as 316 stainless steel for example, carbides tend to readily form at carburization temperatures greater than 1000 °F. Therefore, case hardening processes of the present invention are performed at a temperature less than about 1000 °F for stainless steel alloys. The time period during which carburization takes place also affects carbide formation. Even at temperatures below 1000 °F, carbides can form if the base metal is

15
20

- 6 -

exposed to the carbon source for a long enough period of time. In accordance with another aspect of the invention, carburization is performed below a carbide promoting temperature and for a time period less than that which permits carbides to form. Thus, the invention contemplates a time-temperature profile that substantially prevents the formation of carbides during a case hardening process.

As an example of such a time-temperature profile, carbides readily form in 316 stainless steel above 1000 °F, as fast as within an hour. However, below this temperature, for example in the 800-950 °F range, carbides will not form until about a week or more, particularly at the lower temperature range. This is but one example, and the particular time-temperature profile used in any specific carburization process for preventing carbide formation will depend on a number of factors including but not necessarily limited to the carburization temperature and the alloy chemistry of the base metal.

The general steps of the case hardening process in accordance with the present invention are 1) activating the surface area of the article that is to be carburized; 2) diffusing carbon into the activated surface area; and 3) re-passivating the article.

The passive oxide layer that forms over the stainless steel base metal of the article is a carbon blocking layer. This passive layer forms immediately with exposure of the article to air, and is formed as a chromium oxide layer. In order to carburize the article, however, the article surface needs to be activated.

- 7 -

In one embodiment of the invention, activation is performed by exposing the article to a hydrogen halide gas mixture of hydrogen chloride and nitrogen at atmospheric pressure. The gas mixture, for example, can be 17-100% volume hydrogen chloride or hydrogen fluoride, remainder nitrogen. The article is exposed to the activating gas for a
5 time-temperature profile that stays below that which would promote the formation of carbides. In this example, the article is exposed to the gas mixture for about four hours at a temperature between about 600 °F and 800 °F. After the article has been activated, the diffusion process can begin.

In one embodiment of the invention, the carbon atoms are diffused into the article
10 by exposing the article 10 to a carbon monoxide (CO) gas mixture. Such a gas mixture can be, for example, 0.5-60% volume carbon monoxide, 10-50% volume hydrogen, remainder nitrogen, at one atmosphere. This is performed after activation and without exposing the article to air before the diffusion process is completed. The temperature for diffusion is kept below 1000 °F to prevent the formation of carbides. The
15 carbon atoms diffuse into a solid solution with the base metal. In this example the article is exposed to the CO gas mixture at a temperature in a range of about 750 °F to 950 °F for up to two weeks. The exact time and temperature parameters will vary depending on the base metal, the amount of diffusion required.

Those skilled in the art will understand that the diffusion time period will
20 determine the depth of the carbon hardened surface because diffusion rate is temperature dependent. Since time also is related to the temperature related formation of carbides, the

- 8 -

carburization diffusion process should be controlled to achieve the desired case depth using a time-temperature profile that prevents the formation of carbides for the particular alloy in use. For example, because carbide formation is a function of time and temperature, in cases where a deep case is desired it may be necessary to reduce the temperature during the diffusion process as time goes by to prevent carbide formation. The lower the temperature of diffusion the longer the diffusion process can last without carbides forming. The drawback is the added time it may take to reach a desired diffusion depth. But in many cases, by keeping the carburization temperature below that temperature at which carbides readily form, for example less than 1000 °F for 316 stainless steel, the article can be case hardened to a sufficient depth without carbides forming.

The drawing illustrates in a representative manner the end result after carburization. After the carbon atoms are diffused into the base metal, a case hardened portion 30 of the article 10 has been formed that is harder than the base metal alloy, in this example 316 stainless steel, without the formation of carbides. The relative thickness of the hardened portion 30 is exaggerated in the drawing for clarity, and in practice may only be 0.001 to 0.003 inches, for example. This depth dimension is only one example. After the diffusion is completed and the article exposed to air, a chromium oxide layer again forms on the surface of the article.

An alternative process for the activation step is as follows. In this method, a layer of iron is electroplated onto the entire surface of the article. Conventional electroplating

- 9 -

techniques can be used. The iron layer need not be thick, for example, about 0.0005 inches or less. The iron layer serves several important functions. First, the plating process automatically activates the article. No separate activation step is required. Second, the iron is transparent to carbon atoms therefore the iron layer can remain on the article during the carburization process. Third, the iron layer allows the article to be exposed to air between the activation and diffusion steps because the iron maintains the article in an activated condition.

After the iron layer is disposed on the article, the diffusion process can be performed. The diffusion process can be the same as described herein before. After the article is carburized, the iron plate is removed by any convenient method such as chemical etching. Once the iron is removed, the case hardened article re-passivates upon exposure to air.

Still further embodiments of the invention will next be described. In one method, the article is placed in a conventional plasma oven. The article is placed on the cathode. Air, and especially nitrogen, is then purged from the furnace. Use of the plasma furnace allows for simultaneous activation and carburization of the article. The plasma furnace is used to establish a glow discharge, for example in the range of about 300 to 500 volts DC in a hydrogen bearing carburizing gas mixture of methane, hydrogen, and argon and an elevated time-temperature history that stays below that temperature that would promote the formation of carbides. In this example the process is carried out at about the range of 700 °F to 950 °F for up to two weeks for example. The hydrogen gas activates the article

-10-

by carrying away the oxygen from the oxide layer, and the methane provides the carbon atoms for the carburization diffusion. The carburizing gas mixture can be, for example, 1% volume methane or ethane or propane, and 60% volume hydrogen, remainder argon, at 600 Pa pressure.

5 Another embodiment of the invention involves placing the article in a molten bath of alkali metals (such as, for example, sodium), along with a carbon source such as calcium carbide, within an inert atmosphere of, for example, nitrogen (one atmosphere pressure, for example). The calcium carbide can be, for example, 9-15% weight fo the liquid solution. The liquid sodium activates the entire surface area of the article and the
10 carbon can then diffuse into the base metal. Again, in order to prevent the formation of carbides in the article, the process is carried out at a time-temperature profile below that which promotes carbide formation, and for stainless steel alloys for example, below about 1000 °F. Again, this diffusion process can take several days or weeks depending on the carburization characteristics required.

15 In still a further alternative method, in lieu of the liquid sodium bath the article is placed in a molten bath of cyanide salts such as sodium cyanide for example, and metal halide salts such as a potassium chloride and lithium chloride eutectic for example. The molten bath includes a carbon source such as calcium carbide, and the diffusion process is carried out under an inert non-nitrogen atmosphere such as argon and at a time-
20 temperature profile below that temperature which would promote carbide formation (less than 1000 °F for stainless steel alloys for example). In one example, the molten bath

- 11 -

includes 3-10% weight sodium cyanide, 45-52 % weight potassium chloride, 35-41 % weight lithium chloride and 3-10% calcium carbide. The carburization could take place for example over the period of up to two weeks at 750 °F, for example. Again, the actual time-temperature profile will depend on the various factors identified herein above including the depth of the diffusion required, the base alloy metal chemistry, the carbon source and so forth.

The various processes described herein involving exposing the article to gas can be accomplished with conventional and commonly available equipment such as a pit furnace, as is well known to those skilled in the art.

10 The invention has been described with reference to the preferred embodiment. Obviously, modifications and alterations will occur to others upon a reading and understanding of this specification. It is intended to include all such modifications and alterations insofar as they come within the scope of the appended claims or the equivalents thereof.

- 12 -

CLAIMS

Having thus described the invention, it is claimed:

1. A method for case hardening a chromium bearing alloy article, the method comprising:
5 activating the surface of the article by applying a layer of iron over the surface of the article; and
carburiizing the activated surface at a temperature below a temperature which would produce carbides.
2. The method of claim 1 wherein said activating step comprises
10 electroplating a metal on the surface of the article.
3. The method of claim 1 wherein said carburiizing step comprises exposing said activated surface to a carbon bearing gas.
4. The method of claim 3 wherein said gas comprises carbon monoxide.
5. The method of claim 3 wherein said gas is selected from the following
15 group: carbon monoxide and calcium carbide.
6. The method of claim 1 wherein said carburiizing step is performed at a temperature not greater than about 1000 °F.
7. A method for case hardening a chromium alloy article, the method comprising:
20 activating the surface of the article; and

- 13 -

carburizing the activated surface at a temperature below that temperature which would promote the formation of carbides.

8. The method of claim 7 wherein said activating step comprises disposing a layer of iron over the surface of the article.

5 9. The method of claim 7 wherein said activating step comprises exposing the surface of the article to hydrogen chloride gas.

10. The method of claim 9 wherein the article is exposed to said hydrogen chloride gas in an inert atmosphere.

10 11. The method of claim 7 wherein said activating step comprises placing the article in a plasma furnace and exposing the article to a glow discharge in a hydrogen bearing atmosphere.

12. The method of claim 11 wherein said carburizing step is performed in said plasma furnace during said discharge within an atmosphere containing a carbon source gas.

15 13. The method of claim 12 wherein said carbon source gas comprises methane or ethane or propane.

14. The method of claim 7 wherein said activating step comprises disposing the article in a molten alkali metal bath.

20 15. The method of claim 14 wherein said carburizing step is performed with the article in said molten alkali bath with said bath including a carbon source.

-14-

16. The method of claim 15 wherein said carbon source comprises calcium carbide.

17. The method of claim 7 wherein said activating step comprises disposing the article in a molten bath of cyanide salts and metal halide salts.

5 18. The method of claim 17 wherein said carburizing step is performed with the article in said molten bath with said bath including a carbon source.


19. The method of claim 18 wherein said carbon source comprises calcium carbide.

20. The method of claim 7 wherein said carburizing step is performed at a
10 temperature not greater than about 1000 °F.

21. The method of claim 7 wherein the alloy comprises a chromium bearing nickel or ferrous based alloy.

22. The method of claim 1 wherein said activating step comprises electroplating iron on the article surface.

15 23. The method of claim 1 wherein the alloy comprises a chromium bearing nickel or ferrous based alloy.



INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/US 99/18420

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C23C8/02 C23C8/20 C23C8/22 C23C8/36 C23C8/44
C23C8/46

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 653 822 A (STICKELS CHARLES ARTHUR ET AL) 5 August 1997 (1997-08-05) column 2, line 34-40 column 3, line 8-21; table 1	1-3,7,8, 21-23
A	FR 1 531 285 A (BRISTOL SIDDELEY ENGINES LTD) 4 November 1968 (1968-11-04) page 1, left-hand column, line 1-5,22-33 page 2, left-hand column, line 14-25	7,14,17
A	DE 196 44 153 A (GESCHE ROLAND DR) 30 April 1998 (1998-04-30) column 1, line 5-7,20,21	11
A	US 4 268 323 A (JAKUBOWSKI THOMAS M ET AL) 19 May 1981 (1981-05-19) column 3, line 53-63 column 4, line 15-20; claim 1	14,15
-/-		



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

A document member of the same patent family

Date of the actual completion of the international search

19 April 2000

Date of mailing of the international search report

02/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Joffreau, P-0

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 99/18420

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 837 932 A (DEUTSCHE GOLD-UND-SILBER-SCHNEIDANSTALT) 15 June 1960 (1960-06-15) page 2, line 1-7 —	17,18
A	GB 421 014 A (DEUTSCHE GOLD-UND-SILBER-SCHNEIDANSTALT) 12 December 1934 (1934-12-12) page 2, line 45-52 —	16,19

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int'l. Patent Application No

PCT/US 99/18420

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5653822 A	05-08-1997	NONE	
FR 1531285 A	04-11-1968	NONE	
DE 19644153 A	30-04-1998	NONE	
US 4268323 A	19-05-1981	NONE	
GB 837932 A		NONE	
GB 421014 A		NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.